



FULLCHANCE INDUSTRIAL CO.,LTD

TECHNICAL SPECIFICATIONS

QUALITY : NR ELECTRICAL INSULATION RUBBER MATTING

CODE : ELM 3000

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.6	DIN 53508	1.6
HARDNESS	ASTM D2240	65 ± 5 Sh A	DIN 53505	65 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	710 PSI	DIN 53504	50 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	250%	DIN 53504	250%
ABRASION RESISTANCE (max)	ASTM D5963	400 mm ³	DIN 53516	400 mm ³
COMPRESSION SET (70 ° C/24 hrs/25% set)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE (Angular) min	ASTM D624	101 Lbs/Inch	DIN 53515	18 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 ° C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10 / - 20		+10 / - 20
--- ELONGATION AT BREAK (%)		+10 / - 20		+10 / - 20
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70 ° C		-30° to + 70 ° C
COLOUR		BLACK		BLACK
ELECTRICAL INSULATION ON 6.5 MM (BASE)				
PROOF TEST	IS 15652	WITHSTAND 30 KV FOR 1 MIN		WITHSTAND 30 KV FOR 1 MIN
BREAKDOWN VOLTAGE	IS 15652	NO BREAKDOWN AT 40 KV		NO BREAKDOWN AT 40 KV

Products that this data relates to available in China from:

FULLCHANCE INDUSTRIAL CO.,LTD

H Building, Xinwei 3rd Industrial Zone, Dalang Street, Longhua Town,
Baoan District, Shenzhen City, Guangdong Province,
China P.C.: 518109

Tel:0086-0755-81298065

Fax:0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com