



FULLCHANCE INDUSTRIAL CO.,LTD

GP Rubber Sheet Technical Specification Data

COLOR	BLACK
SURFACE	SMOOTH
TEMP RANGE	-30°F - 210°F
TENSILE	900 PSI
DUROMETER	50 to 65 SHORE A
ELONGATION	270%
FIRE RATED	NO
UV RATED	GOOD
CHEMICAL RESISTENT	EXCELLENT
COMPOSITION	SYNTHETIC BLEND

GP Rubber will resist most oils, not effected by sunlight or harsh environmental extremes. GP Rubber maintains superior flexibility in hot or cold conditions, and also has the resiliency to maintain mechanical stability under heavy loads. ASTMD 2000 tested for light commercial to heavy industrial use for numerous rubber sheet applications.

FULLCHANCE INDUSTRIAL CO.,LTD

H Building,Xinwei 3rd Industrial Zone,Dalang Street,Longhua Town,
Baoan District,Shenzhen City,Guangdong Province,
China P.C.: 518109

Tel:0086-0755-27749405

Fax:0086-0755-28145843

Email: fullchance@fullchance.com

Website: www.rollsheetrubber.com