



FULLCHANCE INDUSTRIAL CO.,LTD

TECHNICAL SPECIFICATIONS

QUALITY : SILICONE RUBBER SHEET CODE: SI 60130

PROPERTIES	TEST METHOD	VALUES	
		FPS UNITS	METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.3	1.3
HARDNESS	ASTM D2240	60 ± 5 Sh A	60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	858 PSI	60 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	200%	200%
COMPRESSION SET (70° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	45%	45%
TEAR RESISTANCE (Angular) min	ASTM D624	95 Lbs/Inch	17 Kg/cm
CHANGE IN PROPERTIES			
HEAT AGEING (72 hrs. AT 100 °C)	ASTM D573		
--- HARDNESS (Pts)		+ 1 (Max)	+ 1 (Max)
--- TENSILE STRENGTH (%)		+ 5 / - 5	+ 5 / - 5
--- ELONGATION AT BREAK (%)		+ 5 / - 5	+ 5 / - 5
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471		
ASTM OIL NO.1		-1%	-1%
ASTM OIL NO.2		+ 7%	+ 7%
ASTM OIL NO.3		+ 17%	+ 17%
CHEMICAL RESISTANCE			
--- OZONE	ASTM D 1149	EXCELLENT	EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT	EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT	EXCELLENT
--- OILS		GOOD	GOOD
--- SOLVENTS		FAIR	FAIR
TEMPERATURE RANGE		-70 °to + 200 °C	-70 °to + 200 °C
COLOUR		BRICK RED	BRICK RED

Products that this data relates to available in China from:

FULLCHANCE INDUSTRIAL CO.,LTD

H Building, Xinwei 3rd Industrial Zone, Dalang Street, Longhua Town,
Baoan District, Shenzhen City, Guangdong Province,
China P.C.: 518109

Tel: 0086-0755-81298065

Fax: 0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com