



FULLCHANCE INDUSTRIAL CO.,LTD

TECHNICAL SPECIFICATIONS

QUALITY : NATURAL RUBBER BLACK (ABRASION RESISTANT SHEET)

CODE: AB 45110

| PROPERTIES | TEST METHOD | VALUES | TEST METHOD | VALUES |
|---|--------------------|------------------|-------------|------------------|
| | | FPS UNITS | | METRIC UNITS |
| SPECIFIC GRAVITY | ASTM D297 | 1.1±0.05 | DIN 53508 | 1.1±0.05 |
| HARDNESS | ASTM D2240 | 45 ± 5 Sh A | DIN 53505 | 45 ± 5 Sh A |
| TENSILE STRENGTH (min) | ASTM D412 | 2137 PSI | DIN 53504 | 150 kg/cm2 |
| ELONGATION AT BREAK (min) | ASTM D412 | 600% | DIN 53504 | 600% |
| ABRASION RESISTANCE (max) | ASTM D5963 | 140 mm3 | DIN 53516 | 140 mm3 |
| COMPRESSION SET (70 °C/24 hrs/25% set) (max) | ASTM D395 METHOD B | 30% | DIN 53517 | 30% |
| TEAR RESISTANCE (Angular) min | ASTM D624 | 168 Lbs/Inch | DIN 53515 | 30 Kg/cm |
| CHANGE IN PROPERTIES | | | | |
| HEAT AGEING (72 hrs. AT 70 °C) | ASTM D573 | | | |
| --- HARDNESS (Pts) | | + 5 (Max) | | + 5 (Max) |
| --- TENSILE STRENGTH (%) | | + 10 / -25 | | + 10 / -25 |
| --- ELONGATION AT BREAK (%) | | + 10 / -25 | | + 10 / -25 |
| VOLUME SWELL : AT 70° C FOR 72 HRS/IN | ASTM D 471 | | | |
| ASTM OIL NO.1 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| ASTM OIL NO.2 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| ASTM OIL NO.3 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| CHEMICAL RESISTANCE | | | | |
| --- OZONE | ASTM D 1149 | FAIR | | FAIR |
| --- DILUTE ACIDS AND BASES | | FAIR | | FAIR |
| --- CONCENTRATED ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- OILS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- SOLVENTS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| TEMPERATURE RANGE | | -30 ° to + 70° C | | -30 ° to + 70° C |
| COLOUR | | RED | | RED |

Products that this data relates to available in China from:

FULLCHANCE INDUSTRIAL CO.,LTD

H Building, Xinwei 3rd Industrial Zone, Dalang Street, Longhua Town,
Baoan District, Shenzhen City, Guangdong Province,
China P.C.: 518109

Tel:0086-0755-81298065

Fax:0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com