



FULLCHANCE INDUSTRIAL CO.,LTD

TECHNICAL SPECIFICATIONS

QUALITY : NATURAL RUBBER (ABRASION RESISTANCE SHEET) PULLEY LAGGING- NR 45115 W

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.12±0.05	DIN 53508	1.12±0.05
HARDNESS	ASTM D2240	45 ± 5 Sh A	DIN 53505	45 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	1282.5PSI	DIN 53504	90 kg/cm2
ELONGATION AT BREAK (min)	ASTM D412	600%	DIN 53504	600%
ABRASION RESISTANCE (max)	ASTM D5963	230 mm3	DIN 53516	230 mm3
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	ASTM D395 METHOD B	35%	DIN 53517	35%
TEAR RESISTANCE (Angular) min	ASTM D624	140 Lbs/Inch	DIN 53515	25 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 20		+ 10 / - 20
--- ELONGATION AT BREAK (%)		+ 10 / - 20		+ 10 / - 20
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 70° C		-40° to + 70° C
COLOUR		BEIGE GREY		BEIGE GREY
BACKING LAYER		GREY COLOR NEOPRENE BONDING		

Products that this data relates to available in China from:

FULLCHANCE INDUSTRIAL CO.,LTD

H Building, Xinwei 3rd Industrial Zone, Dalang Street, Longhua Town,
Baoan District, Shenzhen City, Guangdong Province,
China P.C.: 518109

Tel: 0086-0755-81298065

Fax: 0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com