



# FULLCHANCE INDUSTRIAL CO.,LTD

## TECHNICAL SPECIFICATIONS

### QUALITY : NATURAL RUBBER CODE: NR 50125 R

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.25±0.05	DIN 53508	1.25±0.05
HARDNESS	ASTM D2240	50 ± 5 Sh A	DIN 53505	50 ± 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	926 PSI	DIN 53504	80 kg/cm2
ELONGATION AT BREAK ( min )	ASTM D412	300%	DIN 53504	300%
ABRASION RESISTANCE ( max )	ASTM D5963	140 mm3	DIN 53516	140 mm3
COMPRESSION SET (70°C/24 hrs/25% set) (max)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE ( Angular ) min	ASTM D624	123 Lbs/Inch	DIN 53515	22 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 70°C )	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25		+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25		+ 10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
<b>CHEMICAL RESISTANCE</b>				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		FAIR		FAIR
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70 °C		-30° to + 70 °C
COLOUR		BLACK		BLACK

Products that this data relates to available in China from:

## **FULLCHANCE INDUSTRIAL CO.,LTD**

H Building, Xinwei 3rd Industrial Zone, Dalang Street, Longhua Town,  
Baoan District, Shenzhen City, Guangdong Province,  
China P.C.: 518109

Tel:0086-0755-81298065

Fax:0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com