



FULLCHANCE INDUSTRIAL CO.,LTD

TECHNICAL SPECIFICATIONS

QUALITY : NATURAL RUBBER BLACK (ABRASION RESISTANT SHEET) CODE: SW 64110

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.15	DIN 53508	1.15
HARDNESS	ASTM D2240	60/45/60 ± 5 Sh A	DIN 53505	60/45/60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	2136 PSI	DIN 53504	150 kg/cm2
ELONGATION AT BREAK (min)	ASTM D412	500%	DIN 53504	500%
ABRASION RESISTANCE (max)	ASTM D5963	100 mm3	DIN 53516	100 mm3
COMPRESSION SET (70° C/24 hrs/25% set) (Max)	ASTM D395 METHOD B	30%	DIN 53517	30%
TEAR RESISTANCE (Angular) min	ASTM D624	168 Lbs/Inch	DIN 53515	30 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 °C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25		+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25		+ 10 / -25
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 70 °C		-40 ° to + 70 °C
COLOUR		BLACK/ORANGE/BLACK		BLACK/ORANGE/BLACK

Products that this data relates to available in China from:

FULLCHANCE INDUSTRIAL CO.,LTD

H Building,Xinwei 3rd Industrial Zone,Dalang Street,Longhua Town,
Baoan District,Shenzhen City,Guangdong Province,
China' P.C.: 518109

Tel:0086-0755-81298065

Fax:0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com