



# FULLCHANCE INDUSTRIAL CO.,LTD

## TECHNICAL SPECIFICATIONS

**QUALITY : COMMERCIAL NATURAL RUBBER**

**CODE : ABE 45120**

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.2±0.05	DIN 53508	1.2±0.05
HARDNESS	ASTM D2240	45 ± 5 Sh A	DIN 53505	45 ± 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	1425 PSI	DIN 53504	100 kg/cm <sup>2</sup>
ELONGATION AT BREAK ( min )	ASTM D412	400%	DIN 53504	400%
ABRASION RESISTANCE ( max )	ASTM D5963	150 mm <sup>3</sup>	DIN 53516	150 mm <sup>3</sup>
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	ASTM D395 METHOD B	35%	DIN 53517	35%
TEAR RESISTANCE ( Angular ) min	ASTM D624	112 Lbs/Inch	DIN 53515	20 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 70°C )	ASTM D573			
--- HARDNESS (Pts)		+ 5 / -5 (Max)		+ 5 / -5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
<b>CHEMICAL RESISTANCE</b>				
--- OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70°C		-30° to + 70°C
COLOUR		Bric Red/Blue		

Products that this data relates to available in China from:

## FULLCHANCE INDUSTRIAL CO.,LTD

H Building,Xinwei 3rd Industrial Zone,Dalang Street,Longhua Town,  
Baoan District,Shenzhen City,Guangdong Province,  
China P.C.: 518109

Tel:0086-0755-81298065

Fax:0086-0755-28145843

Email: sales@fullchance.com

Website: www.rollsheetrubber.com